

Main industry segments


Biscuit and Crackers, Bread, Pastry

Applications

Dough belt, Food processing/conveying belt

Special features

Easy release



Product Construction / Design	
Conveying side material	Polyamide (PA)/Cotton (CO) fabric
Conveying side surface	Fabric
Conveying side property	Non-adhesive
Conveying side color	White
Traction layer (material)	Polyamide (PA)/Cotton (CO) fabric
Number of Fabrics	2
Pulley side material	Polyamide (PA)/Cotton (CO) fabric
Pulley side surface	Fabric
Pulley side property	Non-adhesive
Pulley side color	White

Product characteristics	
Antistatically equipped	No
Adhesive free joining method	Yes
Flammability	No specific flammability prevention property
Food suitability, FDA conformance	Yes - acc. to 21CFR parts 170 - 199. Details/restrictions see Habasit food compliance declaration.
Food suitability, USDA recommendations	No use intended
Food suitability, EU conformance	Yes - acc. to Regulation (EC) No. 1935/2004 as well as Regulation (EU) No. 10/2011 and/or other relevant food contact legislation. Details/restrictions see Habasit food compliance declaration.
Other conformance/approval	JFRL passed. Contact your Habasit representative for detailed information.
	Halal certified

Technical data		
Thickness of belt	1.30 mm	0.05 inch
Mass of belt (belt weight)	1.1 kg/m ²	0.225 lb/sqft
Tensile force for 1% elongation (k1% static) per unit of width (Habasit standard SOP3-155)	3.8 N/mm	22 lbf/in
Tensile force for 1% elongation after relaxation (k1% relaxed) per unit of width (Habasit Standard SOP3-155 / EN ISO 21181)	1.2 N/mm	7 lbf/in
Min. operating temperature admissible (continuous)	-30 °C	-22 °F
Max. operating temperature admissible (continuous)	80 °C	176 °F
Coefficient of friction (pulley side / steel driving pulley)	0.15 -	
Coefficient of friction (pulley side / driving pulley with friction cover)	0.35 -	
Coefficient of friction (pulley side / pickled steel slider bed)	0.25 -	
Coefficient of friction (pulley side / phenolic resin slider bed)	0.25 -	
Coefficient of friction (pulley side / stainless steel slider bed)	0.15 -	
Seamless manufacturing width	2400 mm	94.49 inch

Joining related properties

Joining method	
Flexproof 20 x 80	Master joining method for standard applications
Flexproof 10 x 80	Master joining method for nosebar / high stress applications
Thermofix	Optional joining method - not applicable for direct food contact applications acc. to EU and FDA regulations
Mecafast Spiro (plastic spiral and rod system)	Optional joining method

[Link to JDS:](#)

Joining method		Flexproof 20 x 80	Flexproof 10 x 80	Thermofix	Mecafast Spiro (plastic spiral and rod system)
Nosebar radius (minimum)	mm inch		4 0.157		
Pulley diameter (minimum)	mm inch	15 0.59	15 0.59		
Pulley diameter minimum with counter flexion	mm inch	20 0.79	20 0.79		
Admissible tensile force per unit of width	N/mm lbf/in	6.0 34	6.0 34		
Admissible tensile force per unit of width at max. operating temperature	N/mm lbf/in	2.0 11	3.0 17		
Slider bed suitable		Yes	Yes	Yes	Yes
Carrying rollers suitable		Yes	Yes	Yes	Yes
Troughed installation suitable		No	No	No	No
Power turns / curved installations		No	No	No	No
Nosebar suitable		No	Yes		No
Low noise applications		Yes	Yes	Yes	Yes
Metal detector suitable		Yes	Yes	Yes	Yes

All data are approximate values under standard climatic conditions: 23°C/73°F, 50% relative humidity (DIN 50005/ISO 554).

Chemical resistance

Link to 'Chemical resistance information': <http://www.habasit.com/en/chemical-resistance.htm>

Mode of use or conveyance

Horizontal, Inclined

Calculations

For most applications calculation is not required. Should you still need a calculation: please ask Habasit.

Recommendation

Do not go below initial elongation (epsilon) ~ 0.5%, Install the slack belt and tension until running perfectly under the full belt load

For details consult 'Storage and handling requirements for belts and machine tapes' or contact Habasit, Protect belts from sunlight/UV-radiation/dust and dirt. Store spare belts in a cool and dry place and if possible in their original packaging.

This product has not been tested according to ATEX standards (atmospheres with explosion risk - ATEX 95 regulation or EU directive 2014/34/EU) and therefore is subject to user's analysis in the respective environment

Group	Fabric Surface Belts
Sub-Group	Bare Fabric Belts
Item number	H010100453

Disclaimer

Product Application Disclaimer (valid for ALL Habasit products and mentioned on all PDS)

This disclaimer is made by and on behalf of Habasit and its affiliated companies, directors, employees, agents and contractors (hereinafter collectively "HABASIT") with respect to the products referred to herein (the "Products"). SAFETY WARNINGS SHOULD BE READ CAREFULLY AND ANY RECOMMENDED SAFETY PRECAUTIONS BE FOLLOWED STRICTLY! Please refer to the Safety Warnings herein, in the Habasit catalogue as well as installation and operating manuals. All indications / information as to the application, use and performance of the Products are recommendations provided with due diligence and care, but no representations or warranties of any kind are made as to their completeness, accuracy or suitability for a particular purpose. The data provided herein are based on laboratory application with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experience may lead to re-assessments and modifications within a short period of time and without prior notice. EXCEPT AS EXPLICITLY WARRANTED BY HABASIT, WHICH WARRANTIES ARE EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, THE PRODUCTS ARE PROVIDED "AS IS". HABASIT DISCLAIMS ALL OTHER WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT, OR ARISING FROM A COURSE OF DEALING, USAGE, OR TRADE PRACTICE, ALL OF WHICH ARE HEREBY EXCLUDED TO THE EXTENT ALLOWED BY APPLICABLE LAW. BECAUSE CONDITIONS OF USE IN INDUSTRIAL APPLICATION ARE OUTSIDE OF HABASIT'S CONTROL, HABASIT DOES NOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS, INCLUDING INDICATIONS ON PROCESS RESULTS AND OUTPUT.